



STINSON PRESS

PRINTING & PUBLISHING

DTF Heat Pressing Instructions

Pre-press fabric for 5 seconds to ensure any moisture is out.

Heavy pressure/ Hot Peel

Poly 275° for 10 sec

Tri 275° for 10 sec

50/50 290° for 10 sec

Cotton 300° for 10 sec

Hot peel the film and repress with Teflon/Parchment paper for 5-10 seconds depending on material.

Please give us a call if you have any questions. 573-686-6011